



## Technical data

		Substance
Protective and covering fleece		Polypropylene
Membrane		Polyethylene copolymer
Reinforcement		Polypropylene non-woven fabric
Attribute	Regulation	Value
Colour		light grey
Surface weight	EN 1849-2	170 g/m <sup>2</sup> ; 0.56 oz/ft <sup>2</sup>
Thickness	EN 1849-2	0.6 mm ; 24 mils
Water vapor resistance factor $\mu$	EN 1931	23 300
sd value	EN 1931	14 m
sd value, humidity variable	EN ISO 12572	0.25 - >25 m
g value		70 MN-s/g
g value, humidity variable		1.25 - >125 MN-s/g
Vapour permeance	ASTM E96-A	0.23 US perms
Vapour permeance, humidity variable	EN ISO 12572	< 0.13 - 13 US perms
Hydrosafe value (sd)	DIN 68800-2	2 m
Surface burning characteristics	ASTM E84	Class A (Flame Spread 0; Smoke development index 105)
Fire rating	EN 13501-1	E
Outdoor exposure		2 months
Water column	EN ISO 811	> 2 500 mm ; > 8' 2"
Water tightness to liquid water	EN 1928	W1
Tensile strength MD/CD	EN 12311-2	490 N/5 cm / 300 N/5 cm ; 56 lb/in / 34 lb/in
Elongation MD/CD	EN 12311-2	20 % / 20 %
Nail tear resistance MD/CD	EN 12310-1	280 N / 280 N ; 63 lbf / 63 lbf
Durability after artificial ageing	EN 1296	passed
Temperature resistance		permanent -40 °C to 80 °C ; -40 °F to 176 °F
Thermal conductivity		0.04 W/(m·K) ; 0.3 BTU-in/(h·ft <sup>2</sup> ·F)
CE labelling	EN 13984	yes

## Application

For use on the inside of insulation installed between rafters or wall framework, or over a hard subsurface for use underneath exterior insulation in combination with all fibrous insulation materials – including blown-in insulation materials. This membrane can be permanently exposed to diffuse UV light – e.g. in unconverted spaces without inner cladding. It can be used on building components that are diffusion-open to the outside or are diffusion-tight, e.g. pitched, flat or green roofs, after appropriate design calculations have been carried out.

## Advantages

- ✓ Excellent protection against mould and moisture damage to structures thanks to humidity-variable diffusion resistance
- ✓ Can be combined with all fibrous insulation materials
- ✓ Easier handling: can be used with insulation installed between rafters or wall framework and with exterior insulation
- ✓ Protects building structure against weathering during the construction phase for roof pitches of 10° (2.1:12) and higher
- ✓ Protected winter building sites thanks to hydrosafe® behaviour
- ✓ Excellent values in the hazardous substance test, has been tested according to the ISO 16000 evaluation scheme

The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about the application and construction can be found in the pro clima planning documentation. For queries please call the pro clima technical hotline on +49 (0)6202 278245.

**MOLL**  
**bauökologische Produkte GmbH**  
 Rheinalstraße 35 - 43  
 D-68723 Schwetzingen  
 Fon: +49 (0) 62 02 - 27 82.0  
 eMail: info@proclima.de



## General conditions

pro clima INTELLO X PLUS should be installed with the printed side facing the installer. The membrane is to be installed horizontally (parallel to the eave) in a taut manner.

Airtight seals can only be achieved on vapour retarders that have been fitted with no folds or creases. Ventilate regularly and systematically to prevent build-up of excessive humidity (e.g. during the construction phase). Occasional, intermittent ventilation is not sufficient to remove large quantities of moisture due to construction work from a building; use a dryer if necessary.

To avoid condensation formation, the thermal insulation should be installed immediately after airtight adhesion of INTELLO X PLUS. This particularly applies when working in winter.

### Fastening

Overlap the membranes by at least 10 cm (4").

Use fastening staples that are at least 10 mm (3/8") wide and 8 mm (5/16") long to attach the membranes. The membranes can only be fastened in a protected manner in the overlap area. The maximum distance between fasteners is 10 to 15 cm (4"-6"); in the case of blown-in insulation: 5 to 10 cm (2" to 4").

Tested for hazardous substances according to



The information provided here is based on practical experience and the current state of knowledge. We reserve the right to make changes to the recommended designs and processing or to make alterations due to technical developments and associated improvements in the quality of our products. We would be happy to inform you of the current technical state of the art at the time you use our products.

Further information about the application and construction can be found in the pro clima planning documentation. For queries please call the pro clima technical hotline on +49 (0)6202 278245.

**MOLL**  
**bauökologische Produkte GmbH**  
Rheintalstraße 35 - 43  
D-68723 Schwetzingen  
Fon: +49 (0) 62 02 - 27 82.0  
eMail: info@proclima.de

